

Release/Peel Ply 60004

Item number: 02605 00011



Technical data

Description

The **Code 60004** is designed for vacuum bag lay-up composites and metal-to-metal bonding structures and is made from 100 % polyester. The fiber melts at approx. 249°C (480°F) and is resistant to phenolic resin system degradation. The fabric leaves a fine surface impression for priming and secondary bonding. The Peel Ply is available in precision slit widths of 58 inches or less.

Code 60004 is available as:

Peel Ply FIN 060 - NAT Scoured and Heat-Set finish

FIN 064 - LP Low Porosity finish FIN 065 - VLP Very Low Porosity finish

Release Ply FIN 061 - SRB Super Release Blue

An inert, heat stabilized, cross-linked polymer finish

Product	Weight: 81 gram/m ²	Width: 1,52 m	Roll length: 274 lin m
Properties	Characteristics		Test Method
Weight	81 gra	81 gram/m²	
Construction	•	Warp: 47,2 ends/cm Weft: 23,2 picks/cm	
Thickness	0,114 – 0,140 mm		ASTM D1777
Tensile Strength	Warp: 227 N/cm Weft: 280 N/cm		ASTM D5034 (Grab)
pH	4,	5 – 7,0	AATCC-81
Extractable Materia	ls Less tha	n 0,5 %	ASTM D2257 (Petroleum Ethe

Ideal storage condition: Temperature: +5 °C to +50 °C Relative humidity: 45 % to 65 %

Avoid direct sun irradiation, colour change of textile does not lead to quality loss.

The values presented in this data sheet are typical values and are not to be interpreted as product specifications.
The purchaser is not released from the obligation to inspect the incoming goods. Test findings do not indicate the suitability of the product for a concrete application.

COMPOSYST GmbH Am Penzinger Feld 15b D-86899 Landsberg am Lech Germany Phone: Fax: E-mail: Web:

+49 (0) 8191 96363-0 +49 (0) 8191 96363-99 office@composyst.com www.composyst.com

Status 01/2021

© 2020 COMPOSYST GmbH

