

## Peel Ply 52008 NAT

Item number: 02605 00036



## Technical data

**Description** The **Code 52008** is designed for vacuum bag lay-up composites and metal-to-metal bonding structures and is made from 100 % nylon 6.6. The fiber melts at approx. 249°C (480°F) and is not resistant to phenolic resin system degradation.

The fabric leaves a fine surface impression for priming and secondary bonding.

The Peel Ply is available in precision slit widths of 58 inches or less.

**Code 52008 is available as:**

- Peel Ply FIN 060 - NAT Scoured and Heat-Set finish
- Release Ply FIN 067 - SRG Super Release Green  
*An inert, heat stabilized, cross-linked polymer finish*

<b>Product</b>	Weight: 61 gram/m <sup>2</sup>	Width: 1,55 m	Roll length: 274 lin m
<b>Properties</b>	<b>Characteristics</b>		<b>Test Method</b>
Weight	61 gram/m <sup>2</sup>		Nominal
Construction	Warp: 40 ends/cm Weft: 33 picks/cm		Nominal
Thickness	0,11 mm		Nominal
Tensile Strength	Warp: 668 Newtons Weft: 556 Newtons		Nominal
Extractable Materials	Less than 0,5 %		Nominal ( <i>Petroleum Ether</i> )

**Ideal storage condition:** Temperature: +5 °C to +50 °C Relative humidity: 45 % to 65 %  
Avoid direct sun irradiation, colour change of textile does not lead to quality loss.

The values presented in this data sheet are typical values and are not to be interpreted as product specifications. The purchaser is not released from the obligation to inspect the incoming goods. Test findings do not indicate the suitability of the product for a concrete application.