

A5000 P3 Release film

Item number: 02604 00056



Technical data

Description

A5000 is a high temperature fluoropolymer, which has been an aerospace industry standard product for many years.

- Exhibits excellent elongation and release properties, and is suitable for use with all prepreg systems including polyester, epoxy, phenolic and BMI.
- Effective at overcoming bridging on the most difficult of contoured shapes.
- Imparts a gloss finish to moulding surfaces.
- Available with an etched surface on one side to aid bonding to rubber products for use as a localized pressure pad/intensifier.
- Available P3 perforated and non-perforated.

Maximum use temperature: 260 °C

Product		Thickness: 25 µm		Width: 1,53 m		Roll length: 153 lin m	
Properties		Characteristics				Test Method	
Density		2,12 – 2,17 g/m³				ASTM D1505	
Production width		Up to 2 m		-0/+2 %		internal	
Thickness		25 µm & 50 µm		±10 %		ISO 4593	
Tensile Strength at break		MD*: TD*:	24 N/mm² 24 N/mm²		±10 %		ASTM D882
Elongation at break		MD*: TD*:	300 % 300 %		±10 %		ASTM D882
Colour	Red	Perforation P3:		ø = 0,38 mm		Spacing = 6,4 mm (¼")	

Note: The above values are to be understood as reference only.
For any additional advice on the film's suitability in specific applications contact COMPOSYST GmbH technical department.

Storage: To be stored in original packaging only.

*) MD: Machine direction
TD: Transverse direction

The values presented in this data sheet are typical values and are not to be interpreted as product specifications.
The purchaser is not released from the obligation to inspect the incoming goods. Test findings do not indicate the suitability of the product for a concrete application.